

## 1. General:

RQ 235 is an electrically fused, transparent quartz glass. This material specification describes the chemical and physical properties of RQ 235, produced by Raesch Quarz (Germany) GmbH.

## 2. Chemical Properties:

### 2.1 Chemical Composition:

RQ 235 has a purity of at least 99.9% SiO<sub>2</sub>, it contains the following impurities in ppm:

Elements	Al	Ca	Cr	Cu	Fe	K	Li	Mg	Mn	Na	Ni	Ti
Typical	15	0.6	0.01	0.02	0.2	0.5	0.7	< 0.1	< 0.1	0.8	< 0.01	100
Maximal	18	1	0.04	0.05	0.6	1.3	1.1	0.2	0.2	1.5	0.04	

### 2.2 OH-Content:

RQ 235, in its untreated state directly after tube drawing, has an OH content of approximately 120 ppm. Through vacuum annealing, the OH content can be reduced to less than 1 ppm, depending on the wall thickness and annealing duration.

### 2.3 Chemical Resistance:

Quartz glass exhibits exceptionally high inertness to chemical reagents. It is classified as Class 1 for water, alkali, and acid resistance. This chemical durability remains effective even at high concentrations and temperatures. Exceptions include hydrofluoric acid and concentrated phosphoric acid.

### 2.4 Gas Permeability:

At room temperature, quartz glass is virtually impermeable to gases. Depending on their respective diffusion coefficients, helium becomes noticeably permeable at around 180°C, hydrogen at around 300°C, light gases at 600°C, and neon, nitrogen, oxygen, and air at around 1000°C.

## 3. Physical Properties:

### 3.1 Mechanical Properties:

Density	[g/cm <sup>3</sup> ]	2.203
Poisson's ratio	[1]	0.17
Hardness	[Mohs]	5.5 - 6.5
Compressive Strength	[N/mm <sup>2</sup> ]	1150
Tensile Strength	[N/mm <sup>2</sup> ]	50
Bending Strength	[N/mm <sup>2</sup> ]	68
Modulus of Elasticity at 20 °C	[N/mm <sup>2</sup> ]	75000

\* The mechanical properties are significantly influenced by the shape, surface texture, and internal stresses. The table lists typical values

### 3.2 Thermal Properties:

Strain Point	[dPas]	10 <sup>14.7</sup>	[°C]	1167
Annealing Point	[dPas]	10 <sup>13.2</sup>	[°C]	1255
Softening Point	[dPas]	10 <sup>7.6</sup>	[°C]	1760
Working Point	[dPas]	10 <sup>4</sup>	[°C]	1700 - 2100
Transformation Temperature			[°C]	approx. 1200
Boiling Point			[°C]	approx. 2230

Max. working temperature: continuous	[°C]	Up to 1160
Max. working temperature: short-term	[°C]	Up to 1300
Devitrification Range	[°C]	1000 - 1700

Linear Thermal Expansion Coefficient (at 25 - 300°C)	[1/K]	$0.54 \times 10^{-6}$
Thermal Conductivity (at 20°C)	[1/Wm*K]	1.4
Specific Heat (at 50°C)	[J/kg*K]	775

### 3.3 Electrical Properties:

Electrical resistivity	[°C]	20	[Ω*m]	$1 \times 10^{18}$
	[°C]	400	[Ω*m]	$1 \times 10^{10}$
	[°C]	800	[Ω*m]	$6.3 \times 10^6$
	[°C]	1200	[Ω*m]	$1.3 \times 10^5$

Dielectric Strength	[°C]	20	[kV/mm]	25 ... 40
	[°C]	500	[kV/mm]	4 ... 5


Dielectric Constant $\epsilon$ (at 20°C, 1 MHz)	[1]	3.7
Dielectric Loss Factor $\text{tg } \delta$ (at 20°C, 1 MHz)	[1]	$1 \times 10^{-4}$

### 3.4 Optical Properties:

Optical Refractive Index (at $\lambda = 589.3 \text{ nm}$ )	[1]	1.459
---	-----	-------

Required Transmission Values at 1 [mm] Wall Thickness:

Wave length $\lambda$ [nm]	205	220	230	240	254	300	350
Transmission T [%]	< 3	< 20	$40 < T < 65$	> 75	> 85	> 89	> 90



**Company Address:**

Raesch Quarz (Germany) GmbH  
In den Folgen 3  
D-98693 Ilmenau  
Telefon: 0049-3677-4696-0 / Fax 0049-3677-4696-3690  
E-Mail: [info@raesch.net](mailto:info@raesch.net)  
Internet: [www.raesch.net](http://www.raesch.net)

**Relevant Documents:**

Product Specification RQ 235

Change History		
Rev.	Date	Change description
0	01.04.2019	<ul style="list-style-type: none"><li>New Document</li></ul>
1	17.04.2024	<ul style="list-style-type: none"><li>New Logo &amp; Layout</li></ul>